

### PRODUCT DESCRIPTION

Stonclad UT is a dense, liquid-rich, self-priming, textured, four-component, notch-trowel-applied, polyurethane mortar system. Stonclad UT consists of a urethane-urea binder, pigments and graded quartz aggregates. Stonclad UT is a nominal 1/4 in./6 mm system. Stonclad UT is a high-impact resistant mortar which exhibits excellent abrasion, thermal shock, thermal cycling and chemical-resistant characteristics, making it ideal for the food and beverage industry, as well as any other applications requiring these properties.

### SYSTEM OPTIONS

#### Cove Base

To provide for an integral seal at the joint between the floor and the wall, cove bases in heights from 2 to 6 in./5 to 15 cm may be specified.

#### Textures

To find the necessary balance between cleanability and slip resistance, Stonclad UT is offered in two levels of texture. The texture is specified as light or medium.

#### Waterproofing

Where the total system must be waterproofed, the use of Stonhard's Stonproof ME7 membrane system with Texture #3 broadcast to refusal is required with a strict adherence to application instructions.

#### Crack Treatment

When crack treatment is needed due to cracks in the substrate, the use of Stonhard's Stonproof CT5 or RH7 with Texture #3 broadcast to refusal is required with a strict adherence to application instructions.

### PACKAGING

Stonclad UT is packaged in units for easy handling. Each unit consists of:

#### Mortar

- 2 cartons, each containing:
  - 4 foil bags of Isocyanate
  - 4 poly bags of Polyol
- 8 individual bags of Part C-1 aggregate

#### Pigment

- 0.67 cartons containing:
  - 12 bags of Part C-2 pigment packs powder

#### Broadcast

- 3 individual bags of Texture 3 broadcast aggregate for light textured systems
- 4 individual bags of Texture 8 broadcast aggregate for medium textured systems

#### UT Topcoat

- 1 carton containing:
  - 4 foil bags of Hardener
  - 4 poly bags of Resin

### COVERAGE

Each unit of Stonclad UT will cover approximately 190 sq. ft/17.6 sq. m at a nominal thickness of 1/4 in./6 mm.

### STORAGE CONDITIONS

Store all components of Stonclad UT between 60 to 85°F/16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life of the liquids is one year while the C-1 has a 6-month shelf life in the original, unopened container.

### COLOR

Stonclad UT is available in 10 standard colors. Refer to the Stonclad Color Sheet. Contact your local Stonhard representative or Technical Service with any questions.

### PHYSICAL CHARACTERISTICS

Compressive Strength .....	7,700 psi
(ASTM C-579).....	after 7 days
Tensile Strength .....	1,000 psi
(ASTM C-307)	
Flexural Strength .....	2,400 psi
(ASTM C-580)	
Flexural Modulus of Elasticity .....	2.6 x 10 <sup>6</sup> psi
(ASTM C-580)	
Hardness .....	80 to 84
(ASTM D-2240, Shore D)	
Impact Resistance .....	>160 in./lbs.
(ASTM D-2794)	
Abrasion Resistance.....	0.03 gm *
(ASTM D-4060, CS-17)	
Flammability .....	Class 1
(ASTM E-648)	
Thermal Coefficient	
of Linear Expansion.....	1.1 x 10 <sup>-5</sup> in./in.°F
(ASTM C-531)	
Water Absorption.....	< 1%
(ASTM C-413)	
VOC Content.....	UT Mortar - 7 g/l
(ASTM D-2369, Method E).....	UT Topcoat - 53 g/l
Cure Rate .....	6 hours for foot traffic
(@ 77°F/25°C).....	24 hours for normal operations

\* Test samples finished with one coat of high solids urethane coating

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment. Values obtained on field-applied materials may vary and certain test methods can only be conducted on lab-made test coupons.

## SUBSTRATE

Stonclad UT, with the appropriate primer, is suitable for application over concrete, wood, brick, quarry tile, metal or Stonset TG6. For questions regarding other possible substrates, contact your local Stonhard representative or Technical Service.

Note: Stonclad UT is suitable for application over new/green concrete. The concrete must be in place for a minimum of 5 days, be dry and have sufficient strength to handle mechanical preparation.

## SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

## PRIMING

Stonclad UT is a self-priming mortar. No additional primer is necessary.

## MIXING

- Proper mixing is critical for the product to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing using a JB Blender (or equivalent 5 gal. pail mixer) or a larger mortar mixer (e.g., a Bough 3 Batch Mixer) is required.
- See Stonclad UT Directions for further details.

## APPLYING

- Material must be used immediately after mixing.
- A Screed Applicator is used to distribute the mixed Stonclad UT onto the floor.
- Notched finishing trowels and spiked rollers are used to smooth the surface of the material to the required thickness.
- Texture aggregate is then broadcast into the wet mortar.
- After mortar cures, remove excess broadcast aggregate.
- Allow the mortar to cure 6 to 8 hours, then apply the Topcoat.
- Detailed instructions on application and installation can be found in the Stonclad UT Directions.

## PRECAUTIONS

- Use these materials only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body-covering apparel, safety goggles or safety glasses and impermeable gloves are required.
- In case of contact, flush area with water for 15 minutes and seek medical attention. Wash skin with soap and water.
- If material is ingested, immediately contact a physician. **DO NOT INDUCE VOMITING.**

## NOTES

- Use only with adequate ventilation.
- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stonclad Chemical Resistance Guide. If a coating is utilized to seal the Stonclad UT surface, please ensure that you consult the Product Data Sheet for the coating on details regarding chemical resistance of the coating utilized.
- Stonclad UT Part C-1 contains Portland Cement and silica fines. A NIOSH-approved dust/mist respirator is required during mixing. Use only with adequate ventilation.
- Safety Data Sheets for Stonclad UT are available online at [www.stonhard.com](http://www.stonhard.com) under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard products.
- Requests for literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high-gloss coatings are subject to a reduction in gloss, while matte-finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

### IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

06/21

© 2021 Stonhard [www.stonhard.com](http://www.stonhard.com)

# STONHARD®

USA HQ Canada	(800) 257 7953 (800) 263 3112	Mexico Argentina	+(52) 55 9140 4500 +(54) 11 5032 3113	Belgium Dubai, UAE	+(32) 67 49 37 10 +(971) 4 3470460	South Africa India	+(27) 11 254 5500 +(91) 22 28500321	Australia	+(61) 3 9587 7433
------------------	----------------------------------	---------------------	--	-----------------------	---------------------------------------	-----------------------	--	-----------	-------------------